## CHEAPE TECHNOLOGY INTERNATIONAL Ltd

#### 1. Preface

The purpose of this product specification is to provide technical information for the rechargeable Lithium-ion button battery LiR2450.

2. Description and Model

2.1 Description Rechargeable Lithium-ion button battery

2.2 Model LiR2450

3. Specification

3.1 Capacity Nominal 100mAh

Typical 120mAh

3.2 Charging Voltage 4.20V

3.3 Nominal Voltage 3.7V at 0.2C mA

3.4 Standard Charging Method Constant current:50mA Constant voltage 4.20V total 5

3.5 Cut-off Discharge Voltage 3.00V

3.6 Max.Discharge Current 200mA

3.7 Max.Charge Current 100mA

3.8 Cycle Life >500 cycles at 0.2C mA discharge

3.9 Ambient Temperature

for Standard Charge  $0^{\circ}$ C ~  $45^{\circ}$ C

for Discharge  $-20^{\circ}\text{C} \sim 60^{\circ}\text{C}$ 

3.10 Storage

for within the temperature  $-20^{\circ}\text{C} \sim 60^{\circ}\text{C}$ 

for within the humidity  $\leq 75\%$ 

3.11 Energy Density

Wh/L ~200

Wh/Kg ~90

3.12 Weight of Bare Cell ~5.5g

3.13 Charge State Internal Impedance <400m  $\Omega$ 

### 4. Appearance

Appearance shall be free from any remarkable scratch, flaws, rust, discoloration or electrolyte leakage(visible or by smell)

- 5.Standard Test condition
- 5.1 Environment Conditions

# CHEAPE TECHNOLOGY INTERNATIONAL Ltd

### 5.2 Test Equipment

(1) Impedance meter


The impedance meter with AC 1kHz should be used


### 6.Test Procedure and Its Standard

Item	Measureing Procedure	Standard
6.1 Appearance	Visual	No Defect and Leak
6.2 Dimension	Caliper	As item 8
6.3 Weight	Scale	As item 3.12
6.4 Maximum Charge Current	CCCV(Constant Current Constant Voltage)	100mA
6.5 Full charge	CCCV	CC-0.2CmA CV- 4.2V
		total 8h
6.6 Open Circuit Voltage	Within 1hr after full charge,measure Open circuit voltage	>4.15V
6.7 Internal Impedance	Measure the battery with 1kHz AC	<400m Ω
6.8 Discharge Capacity	Within 1hr after full charge, discharge until final discharge, at 0.2C mA and measure the capacity	>100mAh
6.9 Maximum Discharge Current	Until final discharge voltage	200 mA
6.10 Charge/Discharge Cycle Life	Charge:CCCV,CC- 0.2CmA,CV-4.2V total 8h	Discharge capacity
	Discharge:0.2CmA to 3.00V,This charge/discharge shall be repeated 500 times	should be >70% of item 6.8
6.11 Leakage Proof	After full charging,the battery shall	No leakage should be
	be stored at 40±2°C and humidity	observed by visual
	80±5%for 21 days	inspection
6.12 Temperature Characteristics	1)After full charge at 20±5°C ,stand at	•
	-20±2°C for 18h,then discharge	Discharge capacity
	at 0.2C mA and measure the capacity	should be>60% of item
	2)After full charge at 20±5°C ,stand at	6.8 and no abnormality
	55±2°C for 2hrs ,then discharge	on its appearance and
	at 1C mA and measure the capacity	stucture
6.13 Charge Retension	After full charging,stand at 20±5℃	Discharge capacity
	for 28 days,measure the discharge	should be>85% of item

## CHEAPE TECHNOLOGY INTERNATIONAL Ltd

- 7.1 Charge/Discharge Characteristics Charge:CC/CV 4.2V, 50mA(0.5C), total 5h Discharge:50mA(0.5C) Cut-off at 3.00V Temperature:25°C
- 7.3 Temperature Characteristics Charge: CC/CV 4.2V 0.5CA,total 5h Discharge: 0.5CA,Cut-off at 3.00V





7.2 Charge/Discharge Cycle Life Charge:CC/CV 4.2V, 0.2CA, total 8h Discharge:0.2CA,Cut-off at 3.00V Temperature:25°C

8. Dimension(Bare cell) mm

