

# Test Report

**Report No.** ECL01J072676021

Page 1 of 4

**Applicant** CYG WAYON CIRCUIT PROTECTION CO.,LTD

**Address** 1001 SHIWAN 7TH ROAD, SHANGHAI, 201207 P.R. CHINA

**The following sample(s) and sample information was/were submitted and identified by/on the behalf of the client**

**Sample Name** Tin

**Sample Received Date** Nov. 20, 2017

**Testing Period** Nov. 20, 2017 to Nov. 28, 2017

**Test Requested** As specified by client, to test Lead (Pb), Cadmium (Cd), Mercury (Hg), Hexavalent Chromium(Cr(VI)), Antimony(Sb), Beryllium(Be) in the submitted sample(s).

## Test Method

Test Item(s)	Test Method	Measured Equipment(s)
Lead (Pb)	IEC 62321-5:2013 Ed.1.0	ICP-OES
Cadmium (Cd)	IEC 62321-5:2013 Ed.1.0	ICP-OES
Mercury (Hg)	IEC 62321-4:2013 Ed.1.0	ICP-OES
Hexavalent Chromium(Cr(VI))	IEC 62321-7-1:2015	UV-Vis
Antimony(Sb)	Refer to US EPA 3050B:1996 & US EPA 6010D:2014	ICP-OES
Beryllium(Be)	Refer to US EPA 3050B:1996 & US EPA 6010D:2014	ICP-OES

**Test Result(s)** Please refer to the following page(s).



Tested by

*Liu Jie*

Approved by

*Su Hongwei*

Su Hongwei

Senior Laboratory Manager

Centre Testing International Pimbiao(Shanghai) Co., Ltd.

Reviewed by

*Taoying*

Date

Nov. 28, 2017

No. R131279013

No.1996, Xinqiniao Road, Pudong New District, Shanghai, China

# Test Report

Report No. ECL01J072676021

Page 2 of 4

## Test Result(s)

Tested Item(s)	Result	MDL
Lead (Pb)	41 mg/kg	2 mg/kg
Cadmium (Cd)	N.D.	2 mg/kg
Mercury (Hg)	N.D.	2 mg/kg
Hexavalent Chromium(Cr(VI))	N.D. ▼	0.10 µg/cm <sup>2</sup> (LOQ)

Tested Item(s)	Result	MDL
Antimony(Sb)	58 mg/kg	5 mg/kg
Beryllium(Be)	N.D.	10 mg/kg

Tested Sample/Part Description Silvery metal

**Remark:** The sample(s) had been dissolved totally tested for Lead, Cadmium, Mercury, Antimony, Beryllium.  
 -MDL = Method Detection Limit  
 -N.D. = Not Detected (<MDL or LOQ)  
 -mg/kg = ppm = parts per million  
 -LOQ = Limit of Quantification, The LOQ of Hexavalent chromium is 0.10 µg/cm<sup>2</sup>  
 -▼The sample is negative for Cr(VI) – The Cr(VI) concentration is below 0.10 µg/cm<sup>2</sup>.  
 The coating is considered a non-Cr(VI) based coating.


# Test Report

Report No. ECL01J072676021


Page 3 of 4

## Test Process


### 1. Lead (Pb), Cadmium (Cd)




### 2. Mercury (Hg)



### 3. Antimony (Sb), Beryllium (Be)



### 4. Hexavalent Chromium (Cr(VI))



# Test Report

Report No. ECL01J072676021

Page 4 of 4

## Photo(s) of the sample(s)



\*\*\* End of report \*\*\*

The test report is effective only with both signature and specialized stamp. The result(s) shown in this report refer only to the sample(s) tested. Without written approval of CTI, this report can't be reproduced except in full.

有限公司